

Technical data sheet.

Micro C

Product description

Micro C is a finely processed natural anhydrite without additives or stimulators with a reduced content of water of crystallisation.


Information

This technical data sheet is intended to give advice to the best of our knowledge; it replaces any previous technical data sheets. The contents of this technical data sheet are not legally binding.

> Sieve residues (Alpine air jet)

Sieving residue	R 32 µm	20 – 40 %
Sieving residue	R 200 µm	≤ 0.2 %
Average value D50 (CILAS 920 laser granulometer)	approx. 27 µm	

Example of the typical grain structure with the CILAS 920 laser granulometer:



For further information

please contact:

CASEA GmbH
Pontelstraße 3
99755 Ellrich
Germany
P +49 36332 89-100
F +49 36332 89-202
info@casea-gips.de
casea-gips.de

A company of the
REMONDIS Group

> Chemical composition

CaSO ₄	> 90.0 %
Crystal water	< 0.2 %
Moisture	< 0.1 %

> Physical values

Bulk weight	1,300-1,400 g/l
Degree of whiteness	> 80.0

> Logistics and safety notes

Commercial form	bag, big bag and bulk
Shelf life	given dry storage, it can be stored for at least 6 months
Safety notes	see safety data sheet no specific hazards arising from Micro C