

Technical Data Sheet.

Micro A

Description of the product

Micro A is a fine prepared natural anhydrite without any activators or additives
Micro A is used in special fields of building materials

Information


This product data sheet is intended to give advice to the best of our knowledge; it replaces any previous product data sheets. The contents of this product data sheet are not legally binding.

> Particle size distribution

Average value D50 (Horiba LA 350)

ca. 10 μm

Example for a typical particle size distribution measured by Lasergranulometer Horiba LA 350



For further information

please contact:

CASEA GmbH
Pontelstraße 3
99755 Ellrich
Germany
P. +49 36332 89-100
F. +49 36332 89-202
info@casea-gips.de
casea-gips.de

A company of the
REMONDIS Group

> Chemical analysis

CaSO ₄	> 90,0 %
Loss on ignition	< 1,0 %
Moisture	< 0,2 %

> Physical analysis

Bulk density	1000 – 1100 g/l
Whitness L* (HunterLab ColorFlex EZ)	> 80

> Logistic and safety notes

Commercial form	Bags, big-bag and bulk
Shell Life	Can be stored for up to 6 months in dry conditions.
Safety notes	See safety data sheet Micro A presents no hazards.